



ZCAT-X16 Organic Zinc Polyurethane Catalyst

Typical Properties	Appearance	Yellowish transparent liquid
	Density (g/cm ³ , 25°C)	1.075
	Viscosity (mPa.s, 25°C)	6000±2200
	Smell	With special compound smell
Environmental Protection	It does not contain heavy metals, polycyclic aromatic hydrocarbons, phthalates and other restricted components, and can pass strict environmental protection regulations of the United States and the European Union, etc.	
Solubility	Soluble in normal polyurethane raw materials (polyether polyol, plasticizer)	
Applications	It is widely used in polyurethane industry. It can be widely used in aromatic or aliphatic isocyanate systems such as TDI, MDI, HDI and IPDI, etc. It is recommended for polyurethane CASE (elastomers, two component sealants, adhesives, coatings) products, especially recommended for polyurethane plastic runway which cures at normal room temperature.	
Advantages	ZCAT-X16 is an organic zinc catalyst. It does not contain solvents. It has the typical characteristics of zinc catalyst as follows: <ul style="list-style-type: none">▲ Post curing catalyst to shorten forming / demoulding / drying time. If higher catalytic activity is required, it is recommended to use in combination with organic bismuth.▲ It does not promote foaming, and the product has no foam. The unique targeting characteristic of not catalyzing the reaction of trace water with isocyanate can avoid CO₂ bubbles generated by the reaction.▲ Safety and environmental protection, good compatibility. It can be used alone or in combination with other organic metal compounds.	
User's Guide	<ul style="list-style-type: none">● It is recommended to be added into polyol components (material P), preferably after vacuum degassing, and stir evenly.● It is not recommended to add into the components of ISO (Material I) due to the risk of gelation. If necessary, be sure to conduct suitability test first.● The dosage is related to factors such as formula and process. The general dosage is 0.1 ~ 1% of the weight of polyol components (material P).● After use, the tank mouth must be sealed immediately.	
Handling & Storage	Exposure to atmosphere should be avoided. Please store in a cool, dry environment away from sunlight and excessive heat.	
Package	25kg/200kg in HDPE drum	
Shelf Life	The unopened shelf life is 24 months from the date of manufacture. After expiration, it can still be used as usual if qualified by inspection.	

All recommendation and technical information (whether verbal, written or by way of product evaluations), including any suggested formulations contained herein is provided for information purpose only and does not constitute a legal contract as well as suitable for relating to the third party rights. The conditions of your use and application of our products, technical assistance and information are beyond our control. Therefore, no guaranty or warranty for your evaluation is made. Consequently the user assumes all risks in connection with the use and handling of this product based on our technical information and recommendations, final determination of suitability of this product is the sole responsibility of the user. (2019 version)