



Technical Data Sheet

Product Name: Polyurethane Catalyst WCAT-WQ01 for single component latent curing PU system

Typical Properties:

Appearance	colorless transparent liquid
Colour (Fe-Co)	≤ 2
Density (g/cm ³ , 25°C)	1.161
Viscosity (mPa.s, 25°C)	55 ± 30
Odor	With special chemical compound odor

Solubility: Easily soluble in common polyurethane raw materials such as polyether polyol, plasticizer etc.

Eco-friendly Characteristic:

It does not contain restricted heavy metals, polycyclic aromatic hydrocarbons, o-benzene plasticizer and other ingredients, and complies with international and domestic general environmental protection regulations.

Features & Advantage:

WCAT-WQ01 is developed for single component latent curing polyurethane systems with added latent curing agents (coatings/adhesives/laminating adhesives/elastomers, etc.), and based on the principle of crosslinking and curing reaction between water in the environment and isocyanate groups and latent curing agents in the colloid, which can significantly improve the storage stability of single component latent curing systems. It is usually recommended to use with general catalysts for moisture curing, such as WCAT-WS8, WS12, T-12, etc., to significantly accelerate the surface drying and internal drying speed of the material after paving. The characteristics are summarized as follows:

- **The storage period is greatly extended while maintaining low viscosity.** WCAT-WQ01 is inert when the material remains sealed and does not promote the reaction between latent curing agents and isocyanate groups, resulting in stable material storage.
- **Fast surface and internal curing.** During the curing process, WCAT-WQ01 showed a significant effect on promoting the preferred reaction between isocyanates and latent curing agents, effectively promoting the complete reaction of latent curing agents, but at the same time not affecting the reaction rate between isocyanates and water, accelerating surface and internal drying.
- **It is recommended to use in combination with catalysts such as WCAT-WS8 and WS12** to achieve ideal surface and internal drying effect and avoid bubble bulging phenomenon; It is not recommended to use it alone.
- **Environmental protection of materials.** It does not contain restricted heavy metals, polycyclic aromatic hydrocarbons, o-benzene plasticizers and other ingredients.

User's Guide:

- It is recommended to be added after the pre polymerization reaction between MDI/TDI and polyether polyols is complete, and it is not recommended to premix with polyether polyols in advance.
- The usage amount is 0.03-0.1%. Due to differences in packaging equipment and processes of the user, it is recommended to conduct a storage stability test first.
- This product has a certain degree of water absorption. Do not expose it to the air to prevent water absorption. After normal use, it is important to immediately close the tank opening.

Handling & Storage:

Product should be stored in a cool, dry environment away from sunlight, excessive heat and rain.

Package: 25kg/200kg in HDPE drum

Shelf Life: The unopened shelf life is 12 months from the date of manufacture.

All recommendation and technical information (whether verbal, written or by way of product evaluations), including any suggested formulations contained herein is provided for information purpose only and does not constitute a legal contract as well as suitable for relating to the third party rights. The conditions of your use and application of our products, technical assistance and information are beyond our control. Therefore, no guaranty or warranty for your evaluation is made. Consequently the user assumes all risks in connection with the use and handling of this product based on our technical information and recommendations, final determination of suitability of this product is the sole responsibility of the user.